



**Date**  
May 20, 2005

**Our reference**  
05DV4/431/16695/brap

**Page** 1/1

SUPPLEMENT TO CERTIFICATE

Summary of additional tests

The Viton & Butyl Glove (Part-No. R55762, R55531, R55761 for Size 9, 10, 11) was also tested with the four gaseous industrial chemicals using the ASTM F739 permeation criterion of 0.1  $\mu\text{g}/\text{cm}^2/\text{min}$ . The results of these tests are as follows:

- Phosgene : > 480 minutes
- Arsine : > 480 minutes
- Cyanogen Chloride : 110 minutes
- Hydrogen Cyanide : > 480 minutes

SIGNATURES:

A blue ink signature of R.J. van Eenennaam, consisting of a large, stylized 'R' and 'J' followed by a horizontal line.

R.J. van Eenennaam  
Project Manager

A blue ink signature of Dr. S. Van der Gijp, consisting of a stylized 'S' and 'V' followed by a horizontal line.

Dr. S. Van der Gijp  
Head of Department Threat and Protection

b.a. P. van Hooff