



Date
May 20, 2005

Our reference
05DV4/432/16695/brap

Page 2/1

SUPPLEMENT TO CERTIFICATE

Summary of additional tests

The Visor PVC material (Part-No. R54135) was also tested with the four gaseous industrial chemicals using the ASTM F739 permeation criterion of $0.1 \mu\text{g}/\text{cm}^2/\text{min}$. The results of these tests are as follows:

- Phosgene : > 480 minutes
- Arsine : > 480 minutes
- Cyanogen Chloride : > 480 minutes
- Hydrogen Cyanide : > 480 minutes

SIGNATURES:

A blue ink signature of R.J. van Eenennaam, consisting of a stylized 'R' and 'J' followed by a horizontal line.

R.J. van Eenennaam
Project Manager

A blue ink signature of Dr. S. Van der Gijp, featuring a stylized 'S' and 'V' with a horizontal line.

Dr. S. Van der Gijp
Head of Department Threat and Protection

b.a. P. van Hooft